



Star Stretch Heat Transfers

...adding value to your brand.

Star Stretch Transfers are created from a time tested formula of inks and multi-color printing that assures vibrant brand recognition and classy looks that will not fade with either washing or wearing. Stretch Transfers are the ideal solution for stretchable Cotton and Polypique Fabric. They will withstand dry cleaning and home laundering at temperatures up to 140°F / 60°C.

Features and Advantages

- Star Stretch heat transfer for application to stretch endurance fabrics and certain fabrics that are typically difficult to adhere to
- Wide application range withstands heat tolerant fabrics that are susceptible to heat marks at both higher and lower temperatures
- Clear, soft feeling adhesive that lessens the adhesive shadow effect even after home laundering and dry cleaning
- High quality presentation and performance for positive and vibrant brand recognition and reinforcement
- Full multi-color transfers, and a range of metallic options
- Clear polyethylene carrier for simple and precise positioning during application

Information

- Excellent wash resistance that withstands up to 30 home laundering and offers good dry clean resistance
- Tolerates light ironing on transfers
- PVC / Lead and Phthalate free

Highly Recommended for

- Intimate apparel
- Sportswear and performance wear
- Children's wear

For more technical information see reverse page



www.starlabels.in





Star Stretch Heat Transfers

...adding value to your brand.

Technical Information for **Extra Stretch Transfers**

PROPERTIES

Product type	Stretch Transfers
Carrier type	Polyester Film
Colors available	Single or multi-color transfers.
Design requirements	Minimum font size : 5 pt, 0.26mm line width. Customised design. Vector based artwork created in software such as Illustrator, Corel Draw or Freehand
Handling	Flexible and soft
Release characteristics	Hot peel / Cold / Warm peel
Finished products	Cut single / A4 Sheet perforated

TYPICAL APPLICATION PARAMETERS: The above application details provided are guidelines based on Star Labels internal testing. Customers should test all applications on the full range of fabrics before going into production at all times. Larger motifs require longer dwell time. Heat sensitive fabrics require lower temperatures.

	Temperature	Dwell Time	Pressure Applied
Higher temp/shorter dwell time application parameters (Hot Peel)	155°C - 165°C	3-6 seconds	8 - 20 PSI 0.6 -1.4kg/cm ²
Higher temp/shorter dwell time application parameters (Cold/ Warm Peel)	155°C - 165°C	10-12 seconds	8 - 20 PSI 0.6 -1.4kg/cm ²

PERFORMANCE CHARACTERISTICS: Wash performance and durability is dependant upon right application. Customers should test all applications on the full range of fabrics before going into production at all times. Tests should be conducted 36 hours after application process.

Domestic Wash	Up to 140°F / 60°C
Dry Clean	Yes
Ironing	Light ironing only at maximum 285°F / 140° C, keeping the iron always in motion

TYPICAL FABRIC TYPES

	Fabrics or mixed content fabrics with high stretch qualities: Cotton, polyester, and/or nylon mixed with Elastane, Lycra or Spandex
--	---

STORAGE

Storage	Exposure to direct heat, sunlight or high humidity to be avoided. Stacking and dusty storage not recommended. Storage conditions should be 32°F- 86°F / 0°C -30°C with relative humidity of 70% or lower. Shelf life of the product is one year, if stored under these conditions.
---------	--

All information given is based on the results of testing performed by Star Labels. Customers should test any product thoroughly through all relevant processes. Star Labels liability is limited to the replacement value of defective transfers. In no event shall Star Labels be held liable for consequential, indirect or incidental damages. Specifications subject to change without notice.



www.starlabels.in

STAR LABELS PRIVATE LIMITED

Works & Mkt. Office: W-66, MIDC Industrial Area, Rabale Naka, Thane Belapur Rd, Navi Mumbai 400 701.
Tel : +91-22-27601208 / 09 Fax: 27601210 Email: star@starlabels.in

Office Tirupur:

Siddharth B. Kothari, C/o. The Kothari Fabs, 20/22, Jothi Theatre Rd, Valipalayam Ext, Tirupur 641601
Tel: 0421- 2241179 / 4321179 Fax: 0421- 2244038 Cell: 093 4444 1179 Email: startirupur@starlabels.in